



## WHITE OR COLORED POOL PLASTER REPAIR

### E-Z INSTRUCTIONS:

1. Lower water below repair area.
2. Remove loose cement and chip area down at least 3/8" deep. Make sure the edges are chipped straight down (not beveled or slanted). Clean the surface and rinse with water.
3. Add LIQUID CEMENT BONDER to **E-Z PATCH® 1 DRY CEMENT MIX** (use fractions = ¼ of the dry mix to ¼ of the liquid cement bonder, etc.). Now add water and mix until you get the consistency of "mashed potatoes. Use warm water for faster set and cold water to slow set.
- 4a. **CRACK REPAIR:** Crack should be saw-cut & cleaned if not min. 1/8" wide & ¼" deep. Rub **E-Z PATCH® 1** deep into crack and remove excess with a moist sponge.
- 4b. **CHIPS OR LARGER AREAS:** Firmly trowel **E-Z PATCH® 1** filling the area. Trowel again (not as firmly) flat and smooth. Remove excess from edges with a moist sponge. After patch stiffens, trowel again with a moist trowel flat and smooth for finish. **You may refill water the next day.**

To make a Custom Color with any of our cement type repair supplies, use any cement dye.

View our instructional repair video showing how to do this repair at [www.e-zpatch.com](http://www.e-zpatch.com)

### E-Z ANSWERS to some Frequently Asked Questions

- Liquid Bonder is inside the jar
- Product will cure faster in hotter weather, slower in cooler weather
- Product is best stored between 40 degrees F and 90 degrees F

**WARNING:** CONTAINS CEMENT, AN ALKALINE SUBSTANCE IRRITATING TO EYES AND SKIN. CONTAINS ACRYLIC RESIN CEMENT BONDER. SHOULD PRODUCT CONTACT EYES, FLUSH THEM IMMEDIATELY AND REPEATEDLY WITH WATER AND CALL A PHYSICIAN. DO NOT TAKE INTERNALLY. IN CASE OF SKIN CONTACT, RINSE IMMEDIATELY WITH WATER. USE OF RUBBER GLOVES IS RECOMMENDED.

**KEEP OUT OF THE REACH OF CHILDREN**