



PEBBLE PLASTER FOR UNDERWATER OR ABOVE WATER FAST SET REPAIRS

Description: **E-Z Patch® 9 F.S. (Fast Set) Pebble Plaster Repair.** For Fast Set underwater repairs or above water (with water lowered) or repair in cold weather. Allow repair to set hard before swimming or before filling pool. Liquid acrylic bonder is not needed in E-Z Patch 9 F.S. Our formula is stronger than original pool plaster or replaster materials.

Before mixing and applying the repair material, make sure it is the right color and material match! It is sometimes hard to see exactly what the color will be from computer monitor screens.

Take a small amount of dry material out of the repair kit and mix with water to be the consistency of "Putty". Then, wet the existing surface that you are trying to match and compare the wet sample to the wet existing surface. If the material needs to be darker, add a very small amount of E-Z Patch Black Cement Dye and dry mix well. If the material needs to be lighter, add a very small amount of E-Z Patch Titanium Dioxide White Cement Colorant and dry mix well. Both colors are available on our website. You can also use any good cement dye. Repeat this process until the color match is satisfactory.

E-Z INSTRUCTIONS:

UNDER WATER REPAIRS:

1. Remove loose cement and chip area at least 3/8" deep. Make sure the edges are chipped straight down (not beveled or slanted). Clean the surface.
2. Add water sparingly to **E-Z PATCH® 9 F.S. DRY CEMENT MIX** and mix it into a very thick consistency enough to be used within 5 min. Use warm water for even faster set and cold water to slow set.
3. Wait a couple of minutes (until the materials start to harden), place a little more than needed in your hand or plastic bag. Install **E-Z PATCH® 9 F.S.** firmly on the area.
4. Slowly flatten smooth with a trowel = flush with the existing plaster & clean edges with a sponge. Expose the Pebble lightly with a sponge. Slowly back away from repair. **Allow repair to set hard before swimming.**

ABOVE WATER REPAIRS:

1. Follow steps 1. & 2. above, but add a little more water.
- 2a. **CRACK REPAIRS:** Saw-cut crack 3/8" wide & 3/8" deep, clean surface, rub **E-Z PATCH® 9 F.S.** deep into crack and remove excess and expose the Pebble with a moist sponge.
- 2b. **CHIPS OR LARGER AREAS:** Firmly trowel **E-Z PATCH® 9 F.S.** filling the area. Trowel flat and smooth = flush with the existing plaster. Remove excess from edges with a moist sponge. Lightly spray with a water hose, bug sprayer or use a wet

sponge to expose the pebble. If there is any residue "haze" the next day, it can be removed by wetting the surface with water & pouring a mixture of 1/3 muriatic acid to 2/3 water on the patched area. Wait 1 minute and rinse using a water hose.

Allow repair to set hard before filling pool.

To make a Custom Color with any of our cement type repair supplies, use any cement dye.

View our instructional repair video showing how to do this repair at www.e-zpatch.com

E-Z ANSWERS to some Frequently Asked Questions

- **Fast Set formulas do not require Liquid Bonder**
- **Product will cure faster in hotter weather, slower in cooler weather**
- **Product is best stored between 30 degrees F and 110 degrees F**

WARNING: CONTAINS CEMENT, AN ALKALINE SUBSTANCE IRRITATING TO EYES AND SKIN. SHOULD PRODUCT CONTACT EYES, FLUSH THEM IMMEDIATELY AND REPEATEDLY WITH WATER AND CALL A PHYSICIAN. DO NOT TAKE INTERNALLY. IN CASE OF SKIN CONTACT, RINSE IMMEDIATELY WITH WATER. USE OF RUBBER GLOVES IS RECOMMENDED.

KEEP OUT OF THE REACH OF CHILDREN